



Description	Standard	Result
Total thickness	EN428	1.0 mm
Wear layer thickness	EN429	0.1 mm
Weight	EN430	800 g/m ²
Width	EN426	2 m
Length of sheet	EN426	20m

CLASSIFICATION

Fire rating	GB 8624-1997	B1
Toxic testing	GB18586-2001	Good
Electrical resistance	EN1081	> ₁₀ ⁹ -10
Slip resistance dry	EN13893	≥ _{0.3}
Slip resistance wet	EN 51130	R9

PERFORMANCES

Castor chair test	EN425	No damage
Colour fastness	EN ISO 105 -B02	≥ ₆
Chemical products resistance	EN423	Good
Dimensional stability	EN434	<0.40%
Curl resultant to heat	EN 434	≤ ₄ mm
Sound reduction	EN ISO 717/2	Approx. 4 dB
Residual indentation	EN 433	Approx. 0.04mm ~ 0.04 mm
Anti-bacterial and fungicidal		Good
VOC		<10
Surface treatment		PUR