



CHARACTERISTICS	TEST METHOD	RESULT
Peeling strength of laye	EN431	Pass
Shear forces of layers	EN432	Good
Residual indentation after static load	EN433	≤0.10mm
Dimension stability	EN434	Shrinkage≤ 0.25% Curling≤2mm
Fexbility-100mm mandrel	EN435	No Damage
Wear resistance	EN660ASTMF510	≤2.0mm ³
Toxic	EN 71 PART 3	Complies
Colorfestnesstolightfe	EN20105-B02	≤6
Resistance to fire	ASTME84-03	NFPA Class B
Slip resistance	DIN 51130	R9
Bearing a Castor chair	EN425	Suitable
Resistance to chemicals	EN423ASTMF925	Class 0
Performance classification	EN685	23,34,43
GB/T4085、 GB 8624 B1		Pass